

Tape which fixes curing material of flooring floor.

NO.396



Constitution

- Baking : Polyolefin .
- Adhesive : Pressure sensitive acrylic adhesive

Example of usage



Temporary packing and unity of plastic corrugated cardboard.



Temporary fixation of process material and treatment device



Sealing of plastic container

Specialty

- There is almost no paste remainder.
- It can cut easily by hand.

Characteristic

Item□	Unit□	Measurements□
Thickness	mm	0.126
Adhesion strength	N/25mm	8.72
Rewinding force	N/25mm	2.09
Tensile strength	N/10mm	12.6

Doc No. HOU-022-E-1 2013/09/18 1/2

Notes: This data represents examples of measured values, and not guaranteed values. They do not guarantee compatibility with the applications described in these documents. Please confirm compatibility with your application prior to use. We retain all rights, including copyrights, for the contents of these documents. Copying, reprinting and use for purposes other than originally intended are strictly prohibited without our prior expressed permission. Contact details are provided at the end of this document. Please do not hesitate to contact us for any inquiry.

Test method

- According to JIS Z0237 : 2000.

Precautions

- Wipe oil, moisture, and dust off the surface of adherends thoroughly before application.
- The adhesive is pressure-sensitive. Handle it with utmost care.
- Most recommended temperature for adhesion is above 10°C. (If the temperature is below 10°C (like in winter), their initial adhesive strength will be low.)
- Place the original roll of these products horizontally for storage to avoid deformation.
- Keep the products away from high temperatures and humidity, and store them in a dark cool place avoiding direct sunlight.
- Make sure the product is suitable for the application (objective and conditions) before attempting to use. The tape may come off depending on the substrate to which it is applied or conditions under which it is applied.

Doc No. HOU-022-E-1 2013/09/18 2/2

Notes: This data represents examples of measured values, and not guaranteed values. They do not guarantee compatibility with the applications described in these documents. Please confirm compatibility with your application prior to use. We retain all rights, including copyrights, for the contents of these documents. Copying, reprinting and use for purposes other than originally intended are strictly prohibited without our prior expressed permission. Contact details are provided at the end of this document. Please do not hesitate to contact us for any inquiry.