DOUBLE COATED TAPES

D9600

General description

Nitto double coated tape D9600 is a PET carrier tape which consists of a flame-retardant pressure sensitive modified acrylic adhesive, intended for use as a general mounting tape where flame retardancy is required.

Features

- Flame retardant.
- Polyvalent on different substrates.
- Good holding power.
- High temperature resistance.
- High adhesion.
- Dimensional stable liner.
- Easy converting.

Application

Nitto D9600 is a high-performance PET carrier tape offering strong adhesion, thermal stability, and flame-retardant properties. It is engineered to make flame-retardant materials self-adhesive, including foams and decorative laminates, for use in automotive, marine, railway, aerospace, and building & construction applications.
Flame retardance must be evaluated in combination with the material on which it will be used.

Properties

	Typical Value*	**Test Method**
Tape thickness **	0.100 mm	EN 1942
Adhesive type	Modified acrylic	n/a
Release liner type	Siliconized white PE coated paper (125g/m²)	n/a
Carrier type	PET (0.012mm)	n/a
Adhesion to BA steel	1700 cN/20mm	EN 1939/ ISO 29862
Adhesion to ABS	1650 cN/20mm	EN 1939/ ISO 29862
Adhesion to PP	1250 cN/20mm	EN 1939/ ISO 29862
Static shear	1 mm/3h	EN 1943
Saft test	130 °C	+0.5°C, 20x15mm, 200g

*CAUTION: The above are typical values and should not be used in writing specifications.

*** Tape thickness = Total thickness without liner.*
Details of the test methods are described on the customer product specification.

Warranty

The product is guaranteed to be free from defects in material and workmanship at the time of delivery and will be suitable for use for a period of 12 months thereafter, subject to the conditions set out herein.

Availability

Widths: 1350mm.
Lengths: 50m – 100m – 200m
Please contact us for specific dimensions.

Storage conditions

The product should be protected against direct sunlight and extremes in temperature and humidity. Recommended storage and transport conditions are between 15 °C and 30 °C and between 40% and 75% relative humidity. The product should be stored in its original packaging in a well-ventilated room to avoid deterioration, deformation, and contamination. Once removed from its packaging, it should be protected against dust and other impurities. Do not over stack the product, as this may cause deformation.

Application guidelines

- The tape should be applied to clean and dry surface by automatic mechanical means.
- The best lamination conditions are obtained at a temperature between 15°C and 40°C.
- An application pressure of 10-15N/cm² is recommended to apply the tape to the substrate to achieve a sufficient contact area.
- Keep the tape in its individual packaging until use.
- Remove the liner prior to final usage.
- The negative temperature resistance in a static load application is limited to -20°C.
- If you require additional information on technical properties and application as well as product sampling or testing, please contact your local Nitto sales office or at *askyourquestion@nitto.com.*

General conditions of use and precautions

The properties of the product might be adversely affected by various elements such as composition, condition and surface of and impurities in or on the substrate, temperature and humidity during storage, the surrounding environment at and after application and time of exterior use. When the product is used in combination with another material or process, the user shall assure the compatibility of the product in such combination and whether this combination results in the expected performance. The same principle applies in the event of product use in extreme conditions or circumstances, whether at or after the moment of application, including extended exposure to sunlight or extreme temperatures and pressure.

Packaging, transport and storage

During transport and storage the product should always be protected against direct sunlight and extremes in temperature and humidity and contained in its original packaging. Once removed from its packaging, it should be promptly applied and remain shielded from direct sunlight and extreme temperature as well as protected against dust and other impurities.

Liability

Except for its willful misconduct, Nitto Belgium's liability shall be limited to a replacement, a reimbursement or an additional delivery of the product, and shall not exceed the purchase price of the products. In no event shall Nitto be liable in respect of any indirect or consequential damages, including loss of profits. The above limitations of liability shall equally apply if Nitto Belgium has assisted in any manner with the selection, treatment or application of the product. Nitto's liability is limited to the terms and conditions provided in the Product Specification and Nitto's General Terms and Conditions of Sale.

Product information

This datasheet provides a general description of the product properties and application scope.
Full technical details in connection with this product are presented in the customer product specification, which is available upon request.
The information reflected in this datasheet is subject to change and the product described herein may be modified or discontinued without notice.

Nitto Belgium NV has obtained the following certificates

- ISO 9001
- ISO 14001
- ISO 45001