UHMWPE POROUS MATERIAL

SUNMAP LC-T5320T(SMPLC-T5320T)

Features

- As SUNMAP is a porous sintered material having an open-cell structure; it offers the excellent air and moisture permeability.
- As SUNMAP is made of porous UHMWPE having high wear resistance and low friction coefficient the slip properties of SUNMAP is enhanced.
- SUNMAP offers good chemical resistance against typical acids and alkali.
- Antistatic type
- Flat surface (single side) type

Structure



Fig.1 Structure

Applications

- Suction conveyance of ceramic green sheets
- Pick and place of electronic components
- Fixing of LCD panels during cutting
- Fixing of glass/ceramic substrates during cutting
- Fixing of FPC boards during screen printing
- Fixing of semiconductor wafers during dicing
- Fixing of lenses during polishing
- Enhancement of sliders of electronic equipment
- Protection of cables in cable chains and prevention of abrasion of sliders
- Prevention of creaking noise and abrasion inside cars

Notes: This data represents examples of measured values, and not guaranteed values. They do not guarantee compatibility with the applications described in these documents. Please confirm compatibility with your application prior to use. We retain all rights, including copyrights, for the contents of these documents. Copying, reprinting and use for purposes other than originally intended are strictly prohibited without our prior expressed permission.

Properties

Table.1 General properties

Property	Unit	Characteristic value	Test method
Thickness	mm	0.22	–
Air permeability	$cm^3/cm^2/sec$	5.0	JIS L 1096
Pore size	μm	17	–
Porosity	%	30	–
Tensile strength	MPa	12	JIS C 2107
Elongation	%	90	JIS C 2107
Hardness	Shore D	48	ASTM D2240
Adhesive strength	N/25mm	4	JIS C2107
Surface Roughness（Ra）	μm	1.4	JIS B 0601
Coefficient of kinetic friction	–	0.1	JIS K 7125
Surface resistance ratio	Ω/□	1×10^{10}	JIS K 7194

Standard Products Size

Table.2 Sheet type

Thickness（mm）	Width（mm）	Length（mm）
0.22	450	450

Notes: This data represents examples of measured values, and not guaranteed values. They do not guarantee compatibility with the applications described in these documents. Please confirm compatibility with your application prior to use. We retain all rights, including copyrights, for the contents of these documents. Copying, reprinting and use for purposes other than originally intended are strictly prohibited without our prior expressed permission.