


#### **Product Data Sheet**

# NO.903UL

#### **Outline**

Heat-resistant adhesive tape "NITOFLON NO.903UL" consisting of PTFE(polytetrafluoroethylene) film and silicone adhesive layer.

#### **Structure**



#### **Features**

- Superior flame resistance.
- Superior in mold-releasing and sliding property.
- Non-adhesive side of the tape offers excellent characteristics of polytetrafluoroethylene, such as electrical property, resistance to heat, weather, chemical, and water (water-shedding), low friction coefficient and non-adhesiveness.
- Can smoothly adhere, wind, band and seal, just like regular adhesive tapes.

#### **Applications**

- For heat-resistant masking.
- For heat-sealing.
- For heat-resistant electrical insulation

1/3 NO.903UL\_03E

**Notes:** This data represents examples of measured values, and not guaranteed values. They do not guarantee compatibility with the applications described in these documents. Please confirm compatibility with your application prior to use. We retain all rights, including copyrights, for the contents of these documents. Copying, reprinting and use for purposes other than originally intended are strictly prohibited without our prior expressed permission. Contact details are provided at the end of this document. Please do not hesitate to contact us for any inquiry.



### **Product Data Sheet**

## **Standard Products Size**

Table, 1

Thickness(mm)	Width(mm)	Length(m)
0.08		
0.13	5,9,10,13,15,19,20,22,25,30,38,40,50,75,	10
0.18	100,200,250,300,350,400,450	
0.23		

<sup>\*</sup>Contact us for information concerning sizes other than standard sizes.

#### **General Properties**

Table, 2

Describes	Unit	Typical Values			
Properties		0.08t	0.13t	0.18t	0.23t
Thickness	mm	0.08	0.13	0.18	0.23
Tensile strength	N/19mm	55	93	160	210
Elongation	%	180	220	220	220
Peeling strength	N/19mm	5.6	7.1	7.4	8.7
Unwinding force	N/19mm	4.4	5.8	7.1	8.9
Breakdown voltage	KV	8	11	14	15
Surface resistivity	Ω/□	10 <sup>16</sup>			
Volume resistivity	Ω·cm	10 <sup>15</sup>			
Copper corrosion	-	None			
Heat resistance	-	Good			
Coefficient kinetic friction	-	0.1			
Flame Retardant	-	UL510 Flame Retardant (File E34833)			
Color	-	Gray			
Temperature Use Range	°C	-60 to 200			

NO.903UL\_03E

**Notes:** This data represents examples of measured values, and not guaranteed values. They do not guarantee compatibility with the applications described in these documents. Please confirm compatibility with your application prior to use. We retain all rights, including copyrights, for the contents of these documents. Copying, reprinting and use for purposes other than originally intended are strictly prohibited without our prior expressed permission. Contact details are provided at the end of this document. Please do not hesitate to contact us for any inquiry.



#### **Product Data Sheet**

Table. 3

Name of chemicals	Condition	Chemical resistance <sup>1),2)</sup>
20%Sulfuric acid	80°C×24hours	+++
Concentrated sulfuric acid	20°C×6days	-
Concentrated hydrochloric acid	20°C×27days	+++
Concentrated hydrochloric acid	80°C×14hours	+++
Concentrated nitric acid solution	20°C×25days	+++
Glacial acetic acid	15°C×24hours	+
20% Sodium hydroxide (NaOH)	80°C×24hours	-
20% Sodium hydroxide (NaOH)	20°C×17days	++
Ammonia water	20°C×25days	+++
Toluene	80°C×14hours	-
Butanol	20°C×15days	++
Acetone	20°C×15days	+++
Transformer oil	80°C×24hours	+++
Machine oil	20°C×15days	+++

- 1) +++: No change ++: Break away at the edge +: Break away at same part -: Break away completely
- 2) Adherent: Stainless steel (SUS304) Pressure bonding weight: 2Kg
  Sample is dipped into chemical and judged by appearance of tape(NITOFLON)




Fig.1 180 degrees heat resistance

3/3 NO.903UL\_03E

**Notes:** This data represents examples of measured values, and not guaranteed values. They do not guarantee compatibility with the applications described in these documents. Please confirm compatibility with your application prior to use. We retain all rights, including copyrights, for the contents of these documents. Copying, reprinting and use for purposes other than originally intended are strictly prohibited without our prior expressed permission. Contact details are provided at the end of this document. Please do not hesitate to contact us for any inquiry.