SURFACE PROTECTION TAPES

SPV CGP-551 | SPV CGP-572 | SPV CGP-591

General description

SPV CGP series are Surface Protection Tapes suitable to protect heat treatable coatings on glass substrates immediately after coating, during storage, transportation and converting. The products consist of a PE film coated with a pressure sensitive acrylic-based adhesive. These tapes are available in three adhesion levels.

Features

- Stable adhesion
- Different adhesion levels
- Transparent film for substrate identification and inspection
- Easy removability
- Good humidity resistance
- Recyclable film

Application

The SPV CGP series protects heat treatable coatings on glass against mechanical damages, fingerprints, and environmental influences (e.g. humidity, corrosion) during storage, transportation and converting. The stable adhesion strength and a good humidity resistance, makes these products suitable to protect coated glass during handling, washing, grinding, cutting and hole drilling. The CGP series is available in three adhesion levels: medium (CGP-551), high (CGP-572) and very high (CGP-591). These products are easy-to-peel as the adhesion strength drops instantly to a very low level during removal from jumbo glass sheets without damaging the sensitive coating.

Properties

	SPV CGP-551	SPV CGP-572	SPV CGP-591	Test method
Film type	PE film	PE film	PE film	n/a
Adhesive type	Acrylic-based	Acrylic-based	Acrylic-based	n/a
Total thickness	50µm	50µm	50µm	EN 1942
Adhesion to BA steel	70 cN/20mm	150 cN/20mm	300 cN/20mm	EN 1939
Tensile strength MD*	22 N/20mm	22 N/20mm	22 N/20mm	EN 14410
Elongation MD*	250%	250%	250%	
Weatherability on BA steel**	75h	75h	None	ISO 4892-2
Color	Blue translucent	Green translucent	Blue translucent	n/a

CAUTION: The above are typical values and should not be used in writing specifications. Details from the test methods are described on the customer product specification.
* MD = Machine Direction
**The weatherability is measured on BA steel. Depending on the substrate the weatherability performance can be different.

Warranty

The product is guaranteed to be free from defect in material and workmanship at the time of delivery and will be suitable for use for a period of 12 months thereafter, subject to the conditions set out herein.

Availability

Widths: up to 3300 mm
Lengths: 500 m, 1000 m and 3000 m
Please contact us for specific dimensions

Storage conditions

The product should be protected against direct sunlight and extremes in temperature and humidity. Recommended storage and transport conditions are between 15 °C and 30 °C and between 40% and 75% relative humidity. The product should be stored in its original packaging in a well-ventilated room to avoid deterioration, deformation and contamination. Once removed from its packaging, it should be protected against dust and other impurities. Do not over stack the product, as this may cause deformation.

Lamination guidelines

- This tape should be applied to clean and dry surface by automatic mechanical means.
- To avoid entrapped air-bubbles, excessive tension and shear, the customer should determine appropriate lamination conditions.
- The best lamination conditions are obtained at a temperature between 15 °C and 40 °C.

Application guidelines

- In general, these tapes are immediately usable for further processing after lamination.
- SPV CGP-series are not designed for prolonged outside exposure.
- Surface Protection Tapes are not meant for permanent protection, they should be removed at the end of the supply chain.

General conditions of use and precautions

The properties of the product might be adversely affected by various elements such as composition, condition and surface of and impurities in or on the substrate, temperature and humidity during storage, the surrounding environment at and after application and time of exterior use. When the product is used in combination with another material or process, the user shall assure the compatibility of the product in such combination and whether this combination results in the expected performance. The same principle applies in the event of product use in extreme conditions or circumstances, whether at or after the moment of application, including extended exposure to sunlight or extreme temperatures and pressure.

Packaging, transport and storage

During transport and storage the product should always be protected against direct sunlight and extremes in temperature and humidity and contained in its original packaging. Once removed from its packaging, it should be promptly applied and remain shielded from direct sunlight and extreme temperature as well as protected against dust and other impurities.

Liability

Except for its willful misconduct, Nitto Belgium's liability shall be limited to a replacement, a reimbursement or an additional delivery of the product, and shall not exceed the purchase price of the products. In no event shall Nitto be liable in respect of any indirect or consequential damages, including loss of profits. The above limitations of liability shall equally apply if Nitto Belgium has assisted in any manner with the selection, treatment or application of the product. Nitto's liability is limited to the terms and conditions provided in the Product Specification and Nitto's General Terms and Conditions of Sale.

Product information

This datasheet provides a general description of the product properties and application scope.
Full technical details in connection with this product are presented in the customer product specification, which is available upon request.
The information reflected in this datasheet is subject to change and the product described herein may be modified or discontinued without notice.

Nitto Belgium NV has obtained the following certificates

- ISO 9001
- ISO 14001
- ISO 45001