

SCF(Super Clean Foam)

SCF406T

Outline

SCF406T is polypropylene foam materials with adhesive, which can be used as dust-proof, buffer, shock absorber.

This application is mainly for display gasket of electric appliances, communication equipments and other electronic equipments.

Construction



Features

- As SCF406T is the thinner-foam, it shows excellent flexibility even if it is used in a very narrow clearance.
- Thanks to its low compression stress, it will not deform the structures after application.
- It shows excellent conformability to gaps with bumps or curved surfaces.
- The environment impact material is not used and it has almost no impurities, which might contaminate the equipments
- Due to the stiffness secured by its unique micro-cell structure, it shows excellent process ability and workability.

Application

- Electric appliances, electronic equipments: Dust-proof display gasket and lens buffer for digital camera and digital video recorder.
- Communication equipment: Dust-proof display gasket and camera lens buffer for mobile phone.

Notes: This data represents examples of measured values, and not guaranteed values. They do not guarantee compatibility with the applications described in these documents. Please confirm compatibility with your application prior to use. We retain all rights, including copyrights, for the contents of these documents. Copying, reprinting and use for purposes other than originally intended are strictly prohibited without our prior expressed permission. Contact details are provided at the end of this document. Please do not hesitate to contact us for any inquiry.

Doc No. SCF-047-E-2 2024/06/17 1/2

Standard Size

Table-1

Thickness (mm)	Width (mm)	Length (M)
0.23	450	100

*This value includes each thickness of both foam and double-coated tape.

*For other sizes, please contact us.

Properties

● General Properties

Table -2

Property	Unit	Values	Test method
Density ^{*1}	g/cm ³	0.06	JIS K 6767
50% Compression Load ^{*1}	N/cm ²	0.9	
Adhesive strength (90° peeling)	N/20mm	4.7	Substrate: SUS304 Test speed: 300mm/min

* 1 Value is SCF400T's properties.

Cautions

- Place the products longitudinally to avoid deformation.
- Keep the products away from high temperatures and humidity, and store them in a dark cool place avoiding direct sunlight.
- You should perform the test yourself to make sure the product is capable of the application.

Doc No. SCF-047-E-2 2024/06/17 2/2

Notes: This data represents examples of measured values, and not guaranteed values. They do not guarantee compatibility with the applications described in these documents. Please confirm compatibility with your application prior to use. We retain all rights, including copyrights, for the contents of these documents. Copying, reprinting and use for purposes other than originally intended are strictly prohibited without our prior expressed permission. Contact details are provided at the end of this document. Please do not hesitate to contact us for any inquiry.